JIT SILICONES +

100% SILICONE SEALANT

- Primary Use: To fill voids, cracks, crevices as well as conformal coating for connections and terminals
- Self Leveling
- Flexible Long Lasting Seal
- Service Temperature -75°
 F to 350°F
 (400° F Intermittent)
- UV Resistant
- Excellent Weatherability
- Low Odor Cure
- Won't oxidize sensitive metals (brass, copper)
- Removable Nozzle on Cartridges

Standard package sizes:

ITEM #	SIZE	NOTE
10101 (white) 10106 (clear)	3 oz (90ml) tube	12 Blister Pack Tubes per Standard Box
10103 (white) 10108 (clear)	10.1 oz (300ml) Cartridge	12 Cartridges Per Standard Box
10104 (white) 10109 (clear)	5 gallon pail	Plastic Pail
10105 (white) 10110 (clear)	55 gallon drum	Metal Drum

Available from:

JIT Silicones +

P.O. Box 24 Mars, PA 16046 Phone: (855) JIT-PLUS (855) 548-7587

www.jitsiliconesplus.com

Flowable Neutral Cure

Technical Data

JIT *FlowableNeutral Cure* is a one-part, flowable paste that cures to a rubbery solid at room temperature on exposure to water vapor in the air. This Oxime cure RTV (room temperature vulcanizing) silicone is designed to perform at temperatures from -75° F (-60°C) to 350° F (177°C), & intermittently to 400° F (204°C).

HOW TO USE:

- 1. Prepare surface for application of sealant. For proper application, surfaces must be clean & dry.
- 2. Cut top tip of cartridge above threads, attach nozzle and cut to desired opening size.
- 3. Apply with caulking gun holding at 45° angle, pushing sealant ahead of nozzle.
- 4. Complete tooling immediately before a "skin" forms (typically within 10 minutes, but relative humidity will affect this).
- 5. Material cures & bonds in 24 hours with optimum strength achieved in 72 hours at 25°C (77°F) and 50% relative humidity.
- 6. When fully cured, wash surface for food applications.
- 7. After partial usage of container, any sealant remaining in nozzle will cure. Removal of cured plug from nozzle will allow reuse of remaining contents.

Note:

- Cure time is affected by relative humidity, degree of confinement and cross-sectional thickness of the sealant.
- Due to flowable/self leveling nature of this product, not for use on vertical surfaces (material will slump)

Typical Properties - As Supplied

Test	Unit	Result	Method
Color		Clear or White	visual
Spec Gravity		0.98	СТМ
Extrusion Rate	g/min	590-630	ASTM C603

Cure Characteristics - Exposed to air, 25°C (77°F) and 50% relative humidity

Skin-over time	minutes	30	ASTM C679		
Tack-free time	minutes	90	ASTM C679		
Cure time	hours	24	СТМ		
Typical Properties As Cured					

<u> Typical Properties - As Cured</u>

Test	Unit	Result	Method
Durometer, Shore A	points	15	ASTM D2240
Tensile at Break	psi	50	ASTM D412
Elongation at Break	%	150	ASTM D412

Usable Life & Storage

When stored at or below 32°C (89.6°F), this product has a minimum usable life of 24 months from date of production.

Handling Precautions - See SDS (Safety Data Sheet)

CA Residents (PROP 65): WARNING: This product can expose you to chemicals including methanol, which is known to the State of California to cause birth defects or other reproductive harm.



For more information, go to www.P65Warnings.ca.gov

Limited Warranty - Please Read Carefully

The information contained herein is offered in good faith and is believed to be accurate. However, Because

conditions and methods of use of our products are beyond our control, this information should not be used in

substitution for customer's tests to ensure that JIT Silicones + (JIT) products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

JIT's sole warranty is that the product will meet the sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. JIT SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. JIT DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.