

JIT SILICONES +

Construction Silicone Sealant

100% SILICONE SEALANT

- Primary Use:
Construction Sealing
and Bonding
- Flexible Long Lasting Seal
- Service Temperature -75°
F to 350°F
- (400° F Intermittent)
- UV Resistant
- Excellent Weather-ability
- Acetoxy Cure
- Fixed Nozzle Cartridges
with Foil Seal
- non-food applications



Standard package

ITEM #	SIZE	NOTE
17003 (white) 17008 (clear) 17013 (black) 17018 (aluminum) 17023 (almond) 17028 (bronze)*	10.1 oz (300ml) Cartridge	12 Cartridges Per Standard Box
190-12 (white) 190-8 (clear) 190-16 (black) 190-4 (aluminum) 190-20 (almond) 190-14 (bronze)	*20 oz Sausage Pak	20 Sausage Paks per box
190-9 (white) 190-5 (clear) 190-13 (black) 190-1 (aluminum) 190-17 (almond) 190-2 (bronze)	*5 gallon pail	Plastic Pail

* Special request item - minimum quantity required

JIT Silicones +

P.O. Box 24

Mars, PA 16046

Phone: (855) JIT-PLUS (855) 548-7587

www.jitsiliconesplus.com

Available from:

Construction Silicone Sealant

rev. 07-2018

Technical Data

JIT **Construction Silicone Sealant** is a one-part, non-slumping paste that cures to a rubbery solid at room temperature on exposure to water vapor in the air. This acetoxy cure RTV (room temperature vulcanizing) silicone is designed to perform at temperatures from -75°F (-60°C) to 350°F (177°C), & intermittently to 400°F (204°C).

HOW TO USE:

1. Prepare surface for application of sealant. For proper application, surfaces must be clean & dry.
2. Cut nozzle to desired opening and puncture inner seal.
3. Apply with caulking gun holding at 45° angle, pushing sealant ahead of nozzle.
4. Complete tooling immediately before a “skin” forms (typically within 5-10 minutes, but relative humidity will affect this).
5. Material cures & bonds in 24 hours with optimum strength achieved in 72 hours at 25°C (77°F) and 50% relative humidity.
6. After partial usage of container, any sealant remaining in nozzle will cure. Removal of cured plug from nozzle will allow reuse of remaining contents.

Note:

- Cure time is affected by relative humidity, degree of confinement and cross-sectional thickness of the sealant.
- The odor given off during cure is due to the liberation of acetic acid. This odor dissipates as cure progresses and is undetectable upon curing of the material.

Typical Properties - As Supplied

Cure Characteristics - Exposed to air, 25°C (77°F) and 50% relative humidity

Test	Unit	Result	Method
Color		White, Clear, Black, Aluminum, Almond or Bronze	visual
Flow/Slump	inches	<=0.20	ASTM C639
Non-Volatile Content	% by weight	>=85	ASTM C792
Extrusion Rate	g/min	632	ASTM C603
Skin-over time	minutes	5-10	ASTM C679
Tack-free time	minutes	13	ASTM C679
Cure time	hours	24	CTM

Typical Properties - As Cured

Test	Unit	Result	Method
Durometer, Shore A	points	21	ASTM D2240
Tensile at Break	psi	232	ASTM D412
Elongation at Break	%	512	ASTM D412

This product is not suitable for or intended for use in food applications

Usable Life & Storage

When stored at or below 32°C (89.6°F), this product has a minimum usable life of 24 months from date of production.

Handling Precautions - See SDS (Safety Data Sheet)

Limited Warranty - Please Read Carefully

The information contained herein is offered in good faith and is believed to be accurate. However, Because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that JIT Silicones + (JIT) products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

JIT's sole warranty is that the product will meet the sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. JIT SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. JIT DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.